

Index

Page numbers in *italic*, e.g. 12, refer to figures. Page numbers in **bold**, e.g. 346, signify entries in tables.

A

- Actin 346
 - physico-chemical characteristics 353
- Adipic acid 305
- Aerobic biodegradation 3, 12, 12, 151
 - laboratory-simulated aquatic environments 37–40
- Aeromonas caviae* 231
- Agromaterials 340
- Alanine (Ala)
 - biochemical structure 343
 - relative hydrophobicity 342
- Albumins 346, 350–351
 - biopackagings 351
 - physico-chemical characteristics 353
- Alcaligenes eutrophus* 222
- Alcaligenes faecalis* 225
- Alcaligenes latus* 229
- Algae, bioassays for 120
 - influence on growth 121–122, 122
 - species selection 120–121
- Aliphatic polyesters 188
- Aliphatic-aromatic copolymers 196–197, 196
- Aliphatic-aromatic polyesters 303–304
 - commercial products 324
 - Biomax 327, 329–330
 - characteristic data 329–330
 - Eastar Bio 326–327, 329–330
 - Ecoflex 325, 329–330
 - Enpol 327, 329–330
 - degradation mechanisms 307
 - biocorrosion 308
 - biodegradation in the environment 308–310, 309
 - in vivo* degradation 308
 - degradation of aliphatic-aromatic copolyesters
 - anaerobic conditions 318–319
 - aquatic environments 317–318
 - composting 315–316, 318
 - fate of aromatic sequences and risk assessment 319–324, 320, 321, 323
 - polymer-related parameters 311–315, 312, 314
 - soil 316–317, 318
 - degradation of pure aromatic polyesters 310–311
 - development of biodegradability 304–307
 - historical perspective 305
- American Society for Testing and Materials (ASTM) 146, 148
 - ASTM D6002-96 and D6400-99
 - compostability norms 162–163
- Amino acids
 - biochemical structures 343
 - relative hydrophobicity 342
- Amylases 8–9
 - α -amylase 8, 13
 - β -amylase 8–9, 13
- Amylopectin 8, 9, 186–187, 187, 258
 - molecular structure 259
- Amylose 186–187, 186, 258

- Anaerobic biodegradation 4, 12, 12, 151
 - degradation of aliphatic–aromatic copolyesters 318–319
 - laboratory-simulated aquatic environments 40–43
- Aquatic environments 12, 12
 - degradation of aliphatic–aromatic copolyesters 317–318
- Aquatic tests 166
 - MITI test 153
 - preparation of elutriates 119–120
 - Sturm test 151–152, 151
- Arabidopsis thaliana* 236
- Arachin 346
 - physico-chemical characteristics 353
- Arginine (Arg)
 - biochemical structure 343
 - relative hydrophobicity 342
- Armadilidium vulgare* 65
- Asparagine (Asn)
 - biochemical structure 343
 - relative hydrophobicity 342
- Aspartic acid (Asp)
 - biochemical structure 343
 - relative hydrophobicity 342
- Aspartic endopeptidases 7
- Aspergillus niger* lipase (ANL) 388

B

- Bacteria, luminescent 122–123
- BIFA LCA
 - starch polymer films and bags 469–472
 - starch polymer loose fills 440–443, 441, 442, 443, 469–472
- Bioassays 113–114
 - algae 120
 - influence on growth 121–122, 122
 - species selection 120–121
 - daphnia 123
 - earthworms 119
 - higher plants 115, 116
 - special test conditions 117–119, 118
 - test set up and general conditions 115–117
 - luminescent bacteria 122–123
 - result evaluation 123–124
 - result evaluation and limitations 129–130
 - sediment testing 124–125
 - special prerequisites 125
 - biodegradation intermediates 127, 127
 - diversity of microorganism population 128
 - humic substances 128–129
 - nutrients in samples 125–127, 126
- Biobags 499–500
 - biodegradability and cost-efficiency 500–501
- Biodegradability
 - aquatic tests 75
 - definition 73
 - inherent biodegradability 74
- Biodegradability of polymers 1–2, 22
 - definition 2–4
 - aerobic biodegradation 3, 151
 - anaerobic biodegradation 4, 151
 - difficulty in achieving a consensus 2
 - factors 20–21
 - general characteristics 183–184
 - biodegradability classes 185–186
 - molecular size, structure and chemical composition 185
 - naturally biodegradable polymers 186–191
 - synthetic biodegradable polymers 191–198
 - measuring 11–13
 - enzyme assays 13–14
 - field trials 20
 - gas evolution tests 16–18
 - plate tests 14–15
 - radioactive labelling 18
 - respiration tests 15–16

- simulated accelerating environments 18–20
 - mechanisms 5–6, 184–185
 - enzymic hydrolysis 6–10
 - enzymic oxidation 10–11
 - Biodegradation, definition of 73
 - Biological oxygen demand (BOD) 15
 - two-phase test 154
 - Biomax® 195, 327
 - data 329–330
 - Bionelle® 194–195, 303
 - Bioplastics 340
 - BIOPOL™ 190, 303
 - Blends/mixtures of polymers, effect on Biodegradability 21
 - BPI compostability certification 173, 173
 - Butane diol, terephthalic acid and adipic acid (BTA)
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 41–42, 42, 43
 - 3(S)-*sec*-Butyl-morpholine-2,5-dione, ring opening polymerisation 398
- C**
- Candida antarctica* lipase (CAL) 386, 388, 401
 - Candida cylindracea* lipase (CCL) 386
 - Candida rugosa* lipase (CRL) 386
 - ε-caprolactone 305
 - Carbon dioxide evolution test 16–18
 - CARBOTECH LCA
 - starch polymer films and bags 443–445, 444, 467–468
 - starch polymer pellets 435, 436, 439, 467–468
 - Cargill Dow LCA
 - poly(hydroxybutyrate) (PHB) 451
 - Caseins 346, 350
 - glass transition temperature 357
 - main plasticisers 361
 - physico-chemical characteristics 353
 - Casting 204–205
 - Cellobiohydrolases 9
 - Cellophane, film properties 198
 - Cellulases 9–10
 - Certification *see* international and national certification procedures
 - Chemical linkages in polymers, effect on biodegradability 21
 - Chemical oxygen demand (COD) 15
 - Chitosan, oxygen permeability 368
 - Chlorella sp.* 120
 - Cholic acid 387, 388
 - Chromatium vinosum*, PHA synthase 234
 - Chromobacterium violaceum* 224
 - Chromobacterium viscosum* lipase (CVL) 386
 - Chymosin 7
 - Chymotrypsin 7, 13
 - Clear zone technique 14
 - Closed bottle test 154
 - Collagen
 - biopackagings 351
 - glass transition temperature 357
 - physico-chemical characteristics 353
 - Comamonas acidovorans* 225, 227, 228
 - Comité Européen de Normalisation (CEN, European Committee for Standardisation) 146, 148
 - Compost bags 207–208
 - LCA 448
 - Composting 58, 59
 - certification of compostability
 - BPI logo 173, 173
 - DIN-Certco 170–172, 171
 - GreenPla 174, 174
 - OK Compost 172–173, 172, 173
 - other systems 174–175
 - compost degradation tests
 - controlled composting test 154–156, 155, 156, 157
 - mineral bed composting test 157–158

- other tests 158
- compost disintegration tests 163–164
- compostability norms 158–159, 159
 - ASTM D6002-96 and D6400-99 norms 162–163
 - DIN V 54900 norm 161–162
 - European Compostability Norm for Packaging Waste (EN 13432) 159–161
- degradation of aliphatic–aromatic copolyesters 315–316, 318
- ecotoxic effects appearing after degradation 132, 133
- ecotoxic effects appearing during degradation 132–133, 134
- EU developments 490
 - Directive on Biological Treatment of Biodegradable Waste (proposed) 490–492
 - Directive on the Landfill of Waste (99/31/CE) 490
- potential influences of polymers 108–109
- COMPOSTO LCA
 - starch polymer films and bags 445–448, 446, 448, 469–472, 473–474
 - starch polymer loose fills 437–439
- Conglycinin, physico-chemical Characteristics 353
- Copolyesters, melting point 202
- Corn gluten 346, 347
 - biopackagings 351
 - glass transition temperature 357
 - main plasticisers 361
- Corn zein 347–348
 - biopackagings 351
 - glass transition temperature 357
 - oxygen permeability 368
 - physico-chemical characteristics 353
- Cottonseed proteins 346
 - biopackagings 351
 - physico-chemical characteristics 353
- Cutin 40

- Cyclobis(diethylene glycol carbonate), ring opening polymerisation 398
- Cyclobis(hexamethylene carbonate), ring opening polymerisation 398
- 1,4-Cyclohexane dimethanol 305
- Cysteine (Cys)
 - biochemical structure 343
 - relative hydrophobicity 342
- Cysteine endopeptidases (sulfhydryl proteases, thiol proteases) 7

D

- Daphnia, bioassays 123
- Deconstructured starch 262–263
- Deutsches Institut für Normung (DIN, German Normalisation Institute) 146, 148
 - certification of compostability DIN-Certco 170–172, 171
 - DIN V 54900 compostability norm 161–162
- 1,3-Dioxan-2-one, ring opening polymerisation 397
- 1,4-Dioxan-2-one, ring opening polymerisation 397
- Dioxygenases 10
- Directive on Biological Treatment of Biodegradable Waste (proposed) 490–492
- Directive on the Landfill of Waste (99/31/CE) 490
- Dissolved organic carbon (DOC) test 154
- Divinyladipate, enzymic polymerisation 393
- Divinylsebacate, enzymic polymerisation 392–393
- 1,12-Dodecanedicarboxylic acid 305
- Dose–response relationships 111, 112
- Durability, evaluation of 76–79

E

- Earthworms, bioassays 119

- Eastar Bio® 326–327
 data 329–330
 Ecoflex® 44, 195, 325
 data 329–330
 Ecotoxicological aspects of polymer
 biodegradation 103, 133–135, 136–137
 analysis
 need for 103–104
 sample preparation 82
 standards and regulations 104–106,
 107
 animal toxicity 83
 biotest recommendations and standard
 procedures 114–115
 bioassays with higher plants 115–119,
 116
 preparation of elutriates for aquatic
 tests 119–120
 result evaluation 123–124
 sediment testing 124–125
 consequences for investigations 135
 materials intended for environmental
 applications 136
 materials intended for organic
 recovery 135–136
 detection of influences on ecosystems
 106–107
 composting 108–109
 soil and sediment biodegradation
 109–110
 microbial toxicity 83
 pathways and interactions 105
 plant toxicity 83
 research results 130
 ecotoxicity of polymers 131–132
 ecotoxicity of polymers after
 degradation 132, 133
 ecotoxicity of polymers during
 degradation 132–133, 134
 relationship between chemical
 structure, biodegradation pathways
 and potentially toxic metabolites
 130–131
 special prerequisites when applying
 bioassays 125–130
 theoretical background 111
 dose–response relationships 111, 112
 end points 113
 exposure period 112–113
 investigation level 111–112
 profile analysis 114
 test design 111–113
 toxicity tests and bioassays 113–114
Eisenia foetida 119
 Elastase 7
 Elastins, main plasticisers 361
 Enpol® 327
 data 329–330
 Environmental ageing of polymers 80
 Environmental concerns 57
 Environmental niches 150
 Enzyme catalysis 385–386, 419–420
 oxidative polymerisation of phenol and
 derivatives 408–416
 quantitative aspects 409
 SEM images 411
 polyester synthesis 386
 lipase catalysed ring opening and co-
 polymerisation of lactones 406
 polycondensation of hydroxyacids
 and esters 386–388, 387, 388
 polymerisation of dicarboxylic acids
 and derivatives with glycols 388–396,
 389–393
 ring opening co-polymerisation of
 carbonates and cyclic monomers 400
 ring opening polymerisation and co-
 polymerisation of lactones 402–408,
 403
 ring opening polymerisation of
 carbonates and cyclic monomers
 396–401, 396, 397–398
 polysaccharide polymerisation 417–
 419, 418, 419
 Enzymes 5–6
 assays
 applications 13
 drawbacks 14
 principle 13

- enzymic hydrolysis 6
 - esterases 7–8
 - glycosidases 8–10
 - proteases 6–7
- enzymic oxidation 10–11
- Escherichia coli* 221
 - recombinants 235–236
- Esterases 7–8
- Ethylene glycol 305
- Ethylene–acrylic acid copolymer (EAA)/thermoplastic starch composites 263–264
 - effect of ratio 264
- Ethylene–vinyl alcohol copolymer (EVOH)/thermoplastic starch composites 264–267
 - droplet-like structure 265
 - layered structure 266
 - oxygen permeability 368
- EU, composting developments 490
 - Directive on Biological Treatment of Biodegradable Waste (proposed) 490–492
 - Directive on the Landfill of Waste (99/31/CE) 490
- European Committee for Standardisation (CEN, Comité Européen de Normalisation) 146, 148
- European Compostability Norm for Packaging Waste (EN 13432) 159–161
- Exoglucohydrolases 9
- Extrusion of biodegradable polymers 202–204
- F**
- Farming 58–60, 59
- FAT/CARBOTECH LCA 452, 475–476
- Fibre spinning 206
- Ficin 7
- Field trials for assessing biodegradability 20
- Film blowing 204–205
- Finnish compostability certification 175
- Flory equation 262
- Fraunhofer ISI LCA
 - starch polymer pellets 437, 437, 467–468
- Free-Flow Packaging 188, 188
- Fumaric acid 305
- G**
- Gas evolution tests
 - applications 16–17
 - principle 16
 - suitability 17–18
- Gelatin 346, 350
 - biopackagings 351
 - glass transition temperature 357
 - physico-chemical characteristics 353
- German Normalisation Institute (DIN, Deutsches Institut für Normung) 146, 148
 - certification of compostability DIN-Certco 170–172, 171
 - DIN V 54900 compostability norm 161–162
- Gerngross and Slater LCA
 - polyhydroxyalkanoate (PHA) 448–449, 449
- Glass transition temperature 201
 - protein-based materials 357
 - effect of water content 358
 - effect of water content and water activity 359
- Gliadins 346
 - glass transition temperature 357
 - main plasticisers 361
 - physico-chemical characteristics 353
- Globulins 346
 - physico-chemical characteristics 353
- Glucoamylase 9
 - α -glucosidase 9
- Glutamic acid (Glu)
 - biochemical structure 343

- relative hydrophobicity 342
- Glutamine (Gln)
 - biochemical structure 343
 - relative hydrophobicity 342
- Glutelins 346
 - glass transition temperature 357
- Glutenins 346
 - glass transition temperature 357
 - physico-chemical characteristics 353
- Glycine (Gly)
 - biochemical structure 343
 - relative hydrophobicity 342
- Glycinin 346
 - physico-chemical characteristics 353
- Glycolic acid 305
- Glycosidases 8–10
- Greenhouse gas (GHG) emissions 435
- GreenPla compostability certification 174, 174

H

- Heat, effects on polymer degradation 63, 63
- Heyde and Luck LCA
 - polyhydroxyalkanoate (PHA) 449–450, 450
- High-solids environments 12, 12
- Histidine (His)
 - biochemical structure 343
 - relative hydrophobicity 342
- Horseradish peroxidase 408
- Humic substances 128–129
- Hydrogels 294
- Hydrolysis 1
- Hydrophilicity of polymers, effect on biodegradability 21
- Hydroxypropylcellulose, oxygen permeability 368

I

- Industrial applications and market evolution of biodegradable polymers
 - applications 206
 - compost bags 207–208
 - loose-fill packaging 206–207
 - other applications 208–209
 - markers 209–211
 - starch-based materials 271–273
 - supply/demand by region 211
 - modified biodegradable polymers 199–200
 - naturally biodegradable polymers 186–191
 - processability 200–201
 - extrusion 202–204
 - fibre spinning 206
 - film blowing and casting 204–205
 - melting points of thermoplastics 202
 - moulding 205
 - synthetic biodegradable polymers 191–198
 - aliphatic/aromatic copolymers 196–197, 196
- International and national certification procedures 145–147
 - certification 169–170
 - BPI logo 173, 173
 - DIN-Certco 170–172, 171
 - GreenPla 174, 174
 - OK Compost 172–173, 172, 173
 - other systems 174–175
 - norms 149–150
 - aquatic, aerobic biodegradation tests 151–154
 - aquatic, anaerobic biodegradation tests 166
 - as a tool of communication 146
 - compost degradation tests 154–158, 155, 156, 157
 - compost disintegration tests 163–164
 - compostability 158–163, 159
 - environmental niches 150
 - high-solids, anaerobic biodegradation tests 167

- marine biodegradation tests 168
- other biodegradation tests 168–169
- soil biodegradation tests 164–165
- standardisation organisations 147–149, 148
- International Standardisation Organisation (ISO) 147, 148
- 3(S)-Isobutyl-morpholine-2,5-dione, ring opening polymerisation 398
- Isoleucine (Ile)
 - biochemical structure 343
 - relative hydrophobicity 342
- 3(S,6R,S)-Isopropyl-6-methyl-morpholine-2,5-dione, ring opening polymerisation 398
- 3(R)-Isopropyl-morpholine-2,5-dione, ring opening polymerisation 398
- 3(R,S)-Isopropyl-morpholine-2,5-dione, ring opening polymerisation 398
- 3(S)-Isopropyl-morpholine-2,5-dione, ring opening polymerisation 398
- Italy
 - costs of collection routes 507
 - municipal recycling rates 493
 - purity of collected food waste 494
 - waste collection frequencies 505
 - waste collection performances 505
- J**
- Japanese Institute for Standardisation (JIS) 148
- K**
- Keratin
 - biopackagings 351
 - physico-chemical characteristics 353
- L**
- D,D-Lactide, ring opening copolymerisation 400
- D,L-Lactide, ring opening copolymerisation 400
- L,L-Lactide, ring opening copolymerisation 400
- Leucine (Leu)
 - biochemical structure 343
 - relative hydrophobicity 342
- Life cycle assessment (LCA) 238, 240, 457–462
 - categories and subcategories 483, 484
 - key indicators 454–456
 - methodology 431–433
 - goal and scope 432
 - impact assessment 432–433
 - interpretation 433
 - inventory analysis 432
 - other polymers
 - FAT/CARBOTECH LCA 452
 - poly(hydroxybutyrate) (PHB)
 - Cargill Dow LCA 451
 - VTT LCA 451–452, 451
 - polyhydroxyalkanoate (PHA)
 - Gerngross and Slater 448–449, 449
 - Heyde and Luck 449–450, 450
 - significance thresholds 484
 - starch polymers
 - BIFA 440–443, 441, 442, 443
 - CARBOTECH 435, 436, 439, 443–445, 444
 - COMPOSTO 437–439, 445–448, 446, 448
 - Fraunhofer ISI 437, 437
 - study overview
 - CARBOTECH 467–468
 - COMPOSTO 469–472, 473–474
 - FAT/CARBOTECH 475–476
 - Fraunhofer ISI 467–468
 - VTT 475–476
 - study preparation checklist 477–482
- Lignin 11
- Lignin peroxidase 11
- Lipases 8
 - enzymic hydrolysis of PCL 13

- Liquid environments, biodegradation
behaviour of polymers 33–35, 51
 laboratory tests with optimised and defined liquid media 43–46
 laboratory-simulated environments 37
 aerobic liquid environments 37–40
 anaerobic liquid environments 40–43
 standard tests 46–51, 47–49, 50
 sweet water and marine environments
 poly(hydroxyalkanoates) 35–37
- Littering 59
- Loose-fill packaging 206–207
- Luminescent bacteria, bioassays 122–123
- Lysine (Lys)
 biochemical structure 343
 relative hydrophobicity 342
- α -Lytic proteases 7
- M**
- Macro-organisms, effects on polymer degradation 64–65
- Manganese peroxidases 11
- Marine biodegradation tests 168
- MARPOL Treaty 34
- Mater-Bi[®] 187–188, 188, 199, 268–269
 physical properties for film production 273
 physical properties for injection moulding 274
 properties 201
 structures 269
- Metal-containing proteases 7
- Methane evolution test 16–18
- Methionine (Met)
 biochemical structure 343
 relative hydrophobicity 342
- 5-Methyl-5-benzyloxy-carbonyl-1,3-dioxan-2-one, ring opening *co*-polymerisation 400
- 5-Methyl-5-benzyloxy-carbonyl-1,3-dioxan-2-one, ring opening polymerisation 397
- Methylcellulose, oxygen permeability 368
- 6(R,S)-Methyl-morpholine-2,5-dione, ring opening polymerisation 398
- 6(S)-Methyl-morpholine-2,5-dione, ring opening polymerisation 398
- Microbiological degradation of polymers 5
 depolymerisation step 5
 enzymic hydrolysis 6
 esterases 7–8
 glycosidases 8–10
 proteases 6–7
 enzymic oxidation 10–11
 mineralisation step 5
- Mineral bed composting test 157–158
- MITI test 153
- Molecular weight of polymers, effect on biodegradability 21
- Monooxygenases 10
- Moulding 205
- Mulching 59, 64
- Municipal solid waste (MSW) treatment, optimisation of 487, 506–507
 biobags 499–500
 biodegradability and cost-efficiency 500–501
 composting in the EU 490
 Directive on Biological Treatment of Biodegradable Waste (proposed) 490–492
 Directive on the Landfill of Waste (99/31/CE) 490
 cost assessment of optimised schemes 501–504, 503
 collection frequency 504–505
 collection frequency in Italy 505
 collection performance in Italy 505
 costs of collection routes in Italy 507
 diversified collection vehicles 505–506
 optimisation tools 504–506
 European developments 488–490, 489
 source separation of organic waste in Mediterranean countries 492–495

- municipal recycling rates in Italy 493
- municipal recycling rates in Spain (Catalunya) 496
- purity of collected food waste in Italy 494
- purity of collected food waste in Spain (Catalunya) 497

- Myofibrillar proteins 346, 351
 - biopackagings 351
 - glass transition temperature 357
 - main plasticisers 361
 - oxygen permeability 368
 - physico-chemical characteristics 353
- Myosin 346
 - physico-chemical characteristics 353

N

- National certification *see* international and national certification procedures
- Naturally biodegradable polymers 186–191
 - modified products 199–200
- No effect concentration (NOEC) level 109
- Non-biological degradation of polymers 4–5
- Nylon 6, melting point 202
- Nylon 6,6, melting point 202

O

- OECD Coupled Unit test 19
- OK Compost certification 172–173, 172, 173
- Organisation for Economic Co-operation and Development (OECD) 146, 148
- Oxalic acid 305
- Oxidoreductases 10
- Oxybutylene diol 305
- Oxyethylene diols 305
- Oxygenases 10

P

- Papain 7
- Paracoccus denitrificans* 229
- Peanut proteins 346, 349–350
 - biopackagings 351
 - physico-chemical characteristics 353
- Pectin, oxygen permeability 368
- ω -pentadecalactone 400
- Pepsin 7
- Persistence of polymers in the environment 431, 457–462
 - comparative data 433–434
 - key indicators for LCA studies 454–456
 - other polymers 452
 - polyhydroxyalkanoate (PHA) 448–450
 - polylactides (PLA) 451–452
 - starch polymers 434–448
 - LCA categories and subcategories 483, 484
 - LCA checklist 477–482
 - LCA methodology 431–433
 - goal and scope 432
 - impact assessment 432–433
 - interpretation 433
 - inventory analysis 432
 - LCA significance thresholds 484
 - LCA study overview
 - CARBOTECH LCA 467–468
 - COMPOSTO LCA 469–472, 473–474
 - FAT/CARBOTECH LCA 475–476
 - Fraunhofer ISI LCA 467–468
 - VTT LCA 475–476
- PHA synthase 234–235
- Phaeodactylum tricorutum* 120
- Phenol, enzymic oxidative polymerisation 408–416
 - quantitative aspects 409
 - SEM images 411
- Phenylalanine (Phe)
 - biochemical structure 343

- relative hydrophobicity 342
- Photobacterium* sp. 122
- Plate tests
 - applications 14
 - drawbacks 15
 - principle 14
- Poly(butylene adipate)
 - degradation behaviour in laboratory-simulated aerobic liquid environments 39
- Poly(butylene adipate) (SP4/6)
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 41–42, 42, 43
- Poly(butylene sebacate)
 - degradation behaviour in laboratory-simulated aerobic liquid environments 39
- Polybutylene succinate (PBSU) 194–195
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 41
 - pressed sheet properties 195
 - structure 194
- Polybutylene terephthalate (PBT) 304
 - historical development of biodegradability 305
- Poly(ϵ -caprolactone) (PCL) 193–194
 - copolymers with PLA 289
 - degradation behaviour in laboratory-simulated aerobic liquid environments 37–38, 40
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 41–42, 42, 43
 - degradation behaviour in sweet water and marine environments 36
 - enzymic hydrolysis by lipase 13
 - film properties 194
 - melting point 202
 - structure 193
 - typical properties 194
- Poly(ester urethanes)
 - degradation behaviour in sweet water and marine environments 36
- Polyesteramides, melting point 202
- Polyesters
 - 2GT, melting point 202
 - 4GT, melting point 202
 - degradation behaviour in sweet water and marine environments 36–37
 - enzymic synthesis 386
 - lipase catalysed ring opening and copolymerisation of lactones 406
 - polycondensation of hydroxyacids and esters 386–388, 387, 388
 - polymerisation of dicarboxylic acids and derivatives with glycols 388–396, 389–393
 - ring opening co-polymerisation of carbonates and cyclic monomers 400
 - ring opening polymerisation and copolymerisation of lactones 402–408, 403
 - ring opening polymerisation of carbonates and cyclic monomers 396–401, 396, 397–398
 - oxygen permeability 368
- Polyethylene (PE)
 - biodegradability 185
 - degradation behaviour in sweet water and marine environments 36, 37
 - film properties 198
 - high-density (HDPE) 194
 - melting point 202
 - molecular weight 346
 - oxygen permeability 368
 - physical properties 291
 - pressed sheet properties 195
 - production energy requirements 449, 450
 - low-density (LDPE) 194
 - biodegradation products 2
 - film blowing 204
 - film properties 194
 - LCA results 436, 437
 - melting point 202

- molecular weight 346
- oxygen permeability 368
- physical properties 273
- pressed sheet properties 195
- Poly(ethylene adipate)
 - degradation behaviour in laboratory-simulated aerobic liquid environments 39
- Poly(ethylene) glycols (PEG)
 - oxidative degradation 11
- Polyethylene glycol (PEG)-modified *Pseudomonas fluorescens* lipase (PEG-PFL) 386
- Poly(ethylene isophthalate) (PEIP)
 - historical development of biodegradability 305
- Poly(ethylene succinate) (PESU) 194–195
 - degradation behaviour in laboratory-simulated aerobic liquid environments 39
 - structure 194
- Polyethylene terephthalate (PET) 193, 195, 304
 - historical development of biodegradability 305
 - production energy requirements 449
- Polyglycolic acid (PGA) 191–192, 191
- Poly(hexamethylene terephthalate) (PHT)
 - historical development of biodegradability 305
- Poly(hexylene succinate)
 - degradation behaviour in laboratory-simulated aerobic liquid environments 39
- Poly(hydroxy adipate) (PHA)
 - degradation behaviour in laboratory-simulated aerobic liquid environments 40
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 40
- Polyhydroxyalkanoates (PHA) 189, 191, 219–220, 240–241
 - applications 238–240
 - biodegradation 237–238
 - biosynthesis mechanisms 228
 - carbon sources 229–231, 230
 - conditions that promote accumulation in microorganisms 229
 - metabolic pathways 231–234, 232
 - PHA synthase 234–235
 - degradation behaviour in sweet water and marine environments 35–36
 - genetically modified systems
 - recombinant *Escherichia coli* 235–236
 - transgenic plants 236–237
 - persistence in the environment
 - Gerngross and Slater LCA 448–449, LCA 449
 - Heyde and Luck LCA 449–450, 450
 - production by genetically modified systems 235
 - production by other techniques
 - in vitro* 237
 - types 220
 - other copolymers 225–227, 226, 226
 - poly[3-hydroxybutyrate-co-3-hydroxyvalerate] (P[3HB-co-3HV]) 222–224, 223, 223
 - poly[3-hydroxybutyrate-co-4-hydroxyvalerate] (P[3HB-co-4HV]) 224–225, 224, 225
 - poly[R-3-hydroxybutyrate] (P[3HB]) 220–222, 221
 - uncommon constituents 227
- Poly(hydroxybutyrate) (PHB) 188–190, 303
 - degradation behaviour in laboratory-simulated aerobic liquid environments 37–38, 38
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 40–41, 42, 43
 - production energy requirements 450
 - properties 189
- Poly(hydroxybutyrate-co-hydroxyvalerate) (PHBV) 188–190

- degradation behaviour in laboratory-simulated aerobic liquid environments 39
- degradation behaviour in laboratory-simulated anaerobic liquid environments 40–41, 42, 43
- degradation behaviour in sweet water and marine environments 35–36
- melting point 202
- moulding 205
- properties 189
- structure 189
- Poly[3-hydroxybutyrate-co-3-hydroxyvalerate] (P[3HB-co-3HV]) 222–224
 - production 223
 - structure 223
- Poly[3-hydroxybutyrate-co-4-hydroxyvalerate] (P[3HB-co-4HV]) 224–225
 - production 225
 - structure 224
- Poly[R-3-hydroxybutyrate] (P[3HB]) 220–222
 - structure 221
- Poly(lactic acid) (PLA) 191–193, 191, 193, 206, 287, 294
 - applications 294
 - chemical properties 292–294
 - effect of hydrolysis 293
 - degradation behaviour in laboratory-simulated aerobic liquid environments 37–38
 - degradation behaviour in laboratory-simulated anaerobic liquid environments 41
 - film blowing 204–205
 - melting point 202
 - physical properties 291–292, 291
 - optical purity 291
 - synthesis
 - copolymers 289–290
 - functionalised polymers 290
 - homopolymers 287–288
- Poly(lactides) (PLA)
 - persistence in the environment
 - Cargill Dow LCA 451
 - VTT LCA 451–452, 451, 475–476
- Polymer degradation
 - mechanisms 4
 - biological degradation 5–11, 184–185
 - non-biological degradation 4–5
- Poly(methymethacrylate), molecular weight 346
- Polyolefin–starch blends, biodegradation Products 2
- Poly(1,2-propanediyl phthalate) (PPP)
 - historical development of biodegradability 305
- Polypropylene (PP)
 - degradation behaviour in sweet water and marine environments 36
 - melting point 202
 - physical properties for injection moulding 274
- Polypropylene terephthalate (PPT)
 - historical development of biodegradability 305
- Polysaccharides 199
 - enzymic oxidative polymerisation 417–419, 418, 419
- Polystyrene (PS)
 - physical properties 291
 - physical properties for injection moulding 274
 - production energy requirements 449, 450
- Poly(vinyl alcohol) (PVOH) 198
 - biodegradability 185, 191
 - dehydrogenase degradation 13
 - film blowing 205
 - film properties 198
- Poly(vinyl chloride) (PVC), film properties 198

Porcine pancreatic lipase (PPL) 386, 399
Processability of biodegradable polymers
200–201

- extrusion 202–204
- fibre spinning 206
- film blowing and casting 204–205
- melting points of thermoplastics 202
- moulding 205

Proline (Pro)

- biochemical structure 343
- relative hydrophobicity 342

Proteases 6–7

Protein materials 339–340, 347–351

- applications 370–372
- biopackagings 351
- formation 352, 354
 - main plasticisers 361
 - solvent process 352–355
 - thermoplastic process 356–362, 360

main applications pre-1960s 341

physico-chemical characteristics of
proteins 353

properties 362–370

- influence of temperature 366
- influence of water activity 367
- mechanical properties of films 364,
365
- oxygen permeability 368
- physical, chemical and enzymic
treatments 363

protein composition and structure
341–347

- bonding 344
- influence of molecular weight 346,
346
- structural organisation 345

Protomonas extorquens 229

Pseudomonas frugi 234

Pseudomonas oleovorans 227, 233

PHA synthase 234

Pseudomonas putida 233, 234

Pullulanase 9

R

Radioactively labelled polymers 18

Rainfall, effects on polymer degradation
63, 64

Ralstonia eutropha 222, 223, 223, 224,
225, 227, 229

PHA synthase 234

Rayon 193

Respiration tests

- applications 15–16
- principle 15
- suitability 16

Rhodococcus sp. 224

Rhodospirillum rubrum 233

Risk assessments 319–324

S

Scenedesmus subspicatus 120

Sebacic acid 305

Selenastrum capricornutum 120, 128

Serine (Ser)

- biochemical structure 343
- relative hydrophobicity 342

Serine endopeptidases 7

Simulated accelerating environments

- applications 19
- drawbacks 20
- principle 18–19

Skeletonema costatum 120

Soil, biodegradation behaviour of
polymers 33, 57–58

- degradability of polymers
 - biodegradability and environmental
compatibility 73–75
 - environmental ageing 80
 - evaluation of durability 76–79
 - standardisation approach 71–73
 - test methods and criteria 73–80

degradation of aliphatic–aromatic
copolyesters 316–317, 318

- delivery routes 59
 - composting 58, 59
 - farming 58–60, 59
 - littering 59, 60
 - mulching 59, 64
- detection of influences on ecosystems 109–110
- effects on soil-living organisms 81
 - assessing transient and permanent effects 81–82
 - ecotoxicity testing 82–83
 - test material concentration 82
- literature survey 83–84
 - specific materials 85–93
- soil biodegradation tests 164–165
- soil burial test methods 76–77
 - indoor burial 79
 - outdoor burial 77–78, 78
- soil environment 60–62, 62
 - macro-organisms 64–65
 - rainfall 64
 - solar heating 63
 - solar UV irradiation 62–63
 - structural properties 65
 - structure 67
 - surface factors 62–65, 63
 - texture 66
 - underground factors 65–71, 66
- soil physical chemistry
 - biological properties 70–71
 - gas content 70
 - minerals and cation exchange capacity 68
 - pH 69
 - soil organic matter (SOM) 68–69
 - temperature 67–68
 - water 69
- Solar heating, effects on polymer degradation 63, 63
- Solar UV irradiation, effects on polymer degradation 62–63, 63
- Soy proteins 346, 349
 - biopackagings 351
 - main plasticisers 361
 - oxygen permeability 368
 - physico-chemical characteristics 353
- Spain (Catalunya)
 - source separation of organic waste 495, 496
 - food waste 497
- Starch 186–187, 186, 187, 257–258
 - amylases 8–9
 - α -amylase 8
 - β -amylase 8–9
 - amylopectin 8, 9
 - component polymers 258–260
 - FTIR of corn starch 266
 - modified starch-based polymers 200
 - starch-based biodegradable polymers 199–200
 - extrusion 202–203
- Starch-based technology 257–258, 274
 - materials on the market 271–273
 - persistence of starch-based polymers in the environment 434
 - BIFA 440–443, 441, 442, 443, 469–472, 469–472
 - CARBOTECH 435, 436, 439, 443–445, 444, 467–468
 - COMPOSTO 437–439, 445–448, 446, 448, 469–472, 473–474
 - Fraunhofer ISI 437, 437, 467–468
 - starch-based foams 187
 - starch-filled plastics 260–261
 - thermoplastic starch (TPS) 261–270
 - LCA results 436, 437
 - ethylene–acrylic acid copolymer (EAA)/thermoplastic starch composites 263–264, 264
 - ethylene–vinyl alcohol copolymer (EVOH)/thermoplastic starch composites 264–267, 265, 266
- Stereochemistry of polymers, effect on biodegradability 21
- Streptococcus* cysteine proteinase 7
- Sturm test 16, 151–152, 151
- Subtilisin 7
- Succinate polyesters, melting point 202

Succinic acid 305
Sulphydril proteases (cysteine
endopeptidases, thiol proteases) 7
Synthetic biodegradable polymers 191–
198

T

Theoretical oxygen demand (TOC) 15
Thermobifidia fusca 44, 316
Thermoplastically processable starch
(TPPS) 263
Thiocapsa pfennigii, PHA synthase 235
Thiol proteases (cysteine endopeptidases,
sulphydril proteases) 7
Threonine (Thr)
 biochemical structure 343
 relative hydrophobicity 342
Thrombin 7
TONE 303
Toxicity tests and bioassays 113–114
 algae 120
 influence on growth 121–122, 122
 species selection 120–121
 daphnia 123
 earthworms 119
 higher plants 115, 116
 special test conditions 117–119, 118
 test set up and general conditions
 115–117
 luminescent bacteria 122–123
 result evaluation 123–124
 result evaluation and limitations 129–
 130
 sediment testing 124–125
 special prerequisites 125
 biodegradation intermediates 127,
 127
 diversity of microorganism population
 128
 humic substances 128–129
 nutrients in samples 125–127, 126
Transgenic plants 236–237

Tropocollagen, physico-chemical
characteristics 353
Trypsin 7, 13
Tryptophane (Trp)
 biochemical structure 343
 relative hydrophobicity 342
Tyrosine (Tyr)
 biochemical structure 343
 relative hydrophobicity 342

U

UV irradiation, effects on polymer
degradation 62–63, 63

V

Valine (Val)
 biochemical structure 343
 relative hydrophobicity 342
Vibrio fischeri 122
VTT LCA
 poly(hydroxybutyrate) (PHB) 451–
 452, 451, 475–476

W

Wheat gluten 346, 349
 biopackagings 351
 gas barrier properties 369
 glass transition temperature 357
 main plasticisers 361
 oxygen permeability 368
 physico-chemical characteristics 353
Whey proteins
 biopackagings 351
 main plasticisers 361
 physico-chemical characteristics 353

Z

Zahn–Wellens test 154

Zeins 346, 347–348

 biopackagings 351

 glass transition temperature 357

 physico-chemical characteristics 353